

## Product datasheet

# Gjøco Murfärg



Gjøco Murfärg is a matt, permeable paint for outdoor use on mineral substrates. Paint contains effective film conserving agent that counteract mold growth and has good weather resistance. The paint is particularly suitable for masonry, concrete and plaster, both untreated and previously painted. Not suitable for use on super Eternit. When used on concrete and cement, moisture and concrete skin need to be checked. The paint is also suitable for moisture exposed surfaces indoors as in basements, garages etc.

Revised 12.01.2024

Symbols



### Technical data

Type:	Styrene acrylate paint
Color:	White, A, B and C base to be tinted by Gjøcomix
Gloss:	Velvet
Specific gravity:	1.45 kg/l (base white)
Solid content:	41 volume%
Application method:	Brush, roller or airless spray.
Thinner / cleaning agent:	Water
Film thickness, wet:	90-110 mikrometers
Film thickness, dry:	40-50 mikrometers
Recommended spreading rate:	6-9 m <sup>2</sup> /l
Guiding data for airless spray:	
Nozzle:	0.53 mm / 0.021"
Spray angel:	65°-80°
Pressure at nozzle:	mPa 15-18 / 150 - 180 kg/cm <sup>2</sup>
Drying time (23 °C, 50 % R.H.):	Drying time deviates at changes in temperature, air humidity, air circulation and film thickness. Do not paint if there is a risk of dew or rain before the paint film is dry.
Dust dry:	0.5 hour.
Interval between coats:	2 hours.
Minimum application temperature:	+10 °C. Best results are obtained by application at room temperature.

### Pretreatment

The surface must be clean and dry. Clean with Gjøco Hustvätt or Gjøco Krafttvätt to remove grease, dirt and contaminants. Follow the instructions on the

packaging. Old loose paint, loose plaster and dust must be removed by brushing / scraping. It is important that the substrate is firm to get good adhesion. Absorbent, porous or heavily limed surfaces are primed with Gjøco Murseis or Mineral primer. New plastered surfaces should be dried at least 4 weeks before overcoating. All construction deficiencies must be addressed before the painting work begins. Surfaces affected by algae and mold are treated with Gjøco Algrent. Stir well. Contents of tins with different production numbers should be mixed. During unfavourable drying conditions (high humidity, fog, rain, low temperatures), glossy, lightly sticky streaks may occur on the paint film.

**Directions for use**

Gjøco Murfärg is ready for use and must not be thinned. When using Gjøco Murfärg at Eternit, it is recommended to test the adhesion through test painting.

**Storage**

Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.

**Disposal of waste**

Liquid paint must not be emptied into sewers or into nature, but must be delivered to an approved hazardous waste collection point. Empty, clean and dry plastic packaging without handle, can delivered as plastic waste.

**Other information**

Application temperature in air and substrate must be at least + 10°C. Stir well before use. Different production numbers are mixed before use. Replace the lid well after use to prevent spillage and drying. Liquid paint must not be emptied into drains or watercourses, but delivered to the environmental protection station. For more detailed information, look at [www.gjoco.se](http://www.gjoco.se).

**Safety**

See separate safety data sheet. Read the information on the packaging. EU limit value for this product (kat. A/c): 40 g/l (2010). This product contains: <40 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information**

**Gjøco AS**  
Ørvegen 1160, 6639 Torvikbukt  
Telephone: +47 712 91 700  
E-mail: [office@gjoco.no](mailto:office@gjoco.no)

