

Product datasheet

Gjøco Akryl Fasademaling



Gjøco Akryl Fasademaling is a matt, weather-resistant acrylic paint for outdoor use on brick and concrete surfaces. It contains a film-protecting antifungal agent. Use on untreated or previously painted brick, concrete and eternit. When using on concrete and cement elements, any moisture and release coating must be checked. Follow the supplier's recommendations. The product is not recommended on lime-rich plaster. Gjøco Akryl Fasademaling is not intended for floors. The paint has good carbonation-inhibiting properties.


Revised 04.12.2024

Symbols



Technical data

Type:	Pure acrylic paint
Color:	White, A, B, C base
Gloss:	Matte
Specific gravity:	1.3 kg/l
Solid content:	Ca. 42 volum%
Application method:	Brush or roller. Spraying is recommended by professionals.
Thinner / cleaning agent:	Water
Film thickness, wet:	Ca. 120 mikrometers
Film thickness, dry:	Ca. 40 mikrometers
Recommended spreading rate:	4-8 m ² /litre, depending on the substrate.
Guiding data for airless spray:	
Nozzle:	0.021"
Spray angle:	65°-80°
Pressure at nozzle:	150 kg/cm ²
Drying time (23 °C, 50 % R.H.):	
Dust dry:	0.5 hour
Interval between coats:	2 hours
Minimum application temperature:	+5 °C. Low temperatures result in longer drying time, and increased the risk of dew matting etc.
Permeability and carbonation:	Meets the requirements for CO ₂ permeability according to SS EN 1504-2 for surface protection products for concrete. Permeability test according to NS-EN 1062-6: CO ₂ permeability (Barrier) – 9.6 Sd (m) at 50 microns – 102

Pretreatment	The substrate must be clean and dry. Clean with Gjøco Husvask or Gjøco Kraftvask to remove grease and contamination. Follow the instructions on the packaging. Old loose paint, loose plaster and dust must be removed by brushing/scraping. It is important that the substrate is firm to achieve satisfactory adhesion. Absorbent, porous or heavily chalked substrates must be primed with Gjøco Primer for masonry and concrete. Plaster work should cure for a minimum of 4 weeks before repainting. All construction defects must be remedied before painting work begins.
Directions for use	Gjøco Akryl Fasademaling is ready to use and should not normally be thinned. When using Gjøco Akryl Fasademaling on eternit, it is recommended that adhesion is tested by applying a test coat.
Color	Use the same batch number on the same coat and the same surface to avoid shade differences in the color. Buckets where the color is mixed on different mixing machines and/or at different times can give shade differences. Be aware of this if more paint is needed for the same project afterwards.
Storage	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
Disposal of waste	Liquid paint must not be emptied into sewers or into nature, but must be delivered to an approved hazardous waste collection point. Empty, clean and dry plastic packaging without handle, can delivered as plastic waste.
	
Other information	Stir well. Different batch numbers are mixed before use for the last coat to avoid gloss and color difference. The paint must not be exposed to frost. Akryl Fasademaling is not suitable for Supereternitt. Packaging sizes: 2.7 and 9 liters
Safety	See separate safety data sheet. Read the information on the packaging. EU limit value for this product (kat. A/c): 40 g/l (2010). This product contains: <30 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information
Gjøco AS
 Ørvegen 1160, 6639 Torvikbuk
 Telephone: +47 712 91 700
 E-mail: office@gjoco.no

