## **Product datasheet**

## Gjøco Fashion 40





Gjøco Fashion 40 is a water-thinnable, low-odor oil paint for indoor use. It has good application properties and provides a durable and elegant finish. It is used as an intermediate and top coat on panels, MDF, doors, windows, frames, moldings and furnishings.

| Revised | 07.10.2025 | 1                      |                  |   |     |   |
|---------|------------|------------------------|------------------|---|-----|---|
| Symbols | MINTEL S   | IKKE<br>UNDER<br>+10°C | VANN-<br>TYNNBAR | 9 | W ( | 9 |

|                | - 1 M                               |  |
|----------------|-------------------------------------|--|
| Technical data | Type:                               | Water-thinned polyurethane modified oil paint  |
|                | Color:                              | White, A, B and C base, colors are mixed over Gjøcomix.  |
|                | Gloss:                              | Matt 05  |
|                | Viscosity:                          | 65-80 P  |
|                | Specific gravity:                   | CA. 1,1 – 1.3 kg/l   |
|                | Solid content:                      | 35 – 37 volum%   |
|                | Application method:                 | Brush, roller, or spray. Spraying should be done by professionals.   |
|                | Thinner/ cleaning agent:            | Water  |
|                | Recommended film thickness, wet:    | 100 – 120 mikrometer   |
|                | Recommended film thickness, dry:    | 40 mikrometer  |
|                | Recommended spreading rate:         | 8 – 10 m²/litre  |
|                | Recommended data for airless spray: |  |
|                | Nozzle tip:                         | 0.20-0.36 mm (0.008-0.014")  |
|                | Spray angle degrees:                | 50°-80°  |
|                | Pressure at nozzle:                 | 15 MPa (150 kg/cm²)  |
|                |                                     | The choice of nozzle, fan angle, and pressure must be adjusted to the specific spray equipment and substrate.                            |
|                | Drying times (23 °C, 50 % R.H.):    |  |
|                | Dry to use:                         | 1 – 2 hours  |
|                | Interval between coats:             | 6 hours. Full adhesion is achieved after 4 weeks of thorough curing.  Varies with changes in temperature, humidity, ventilation and film |

thickness.

|                    | Minimum application temperature: +10 °C. Best results are achieved when applied at room temperature (over +20 °C).   |  |  |  |  |
|--------------------|--|--|--|--|--|
|                    |  |  |  |  |  |
| Pretreatment       | The substrate must be clean and dry. Previously painted surfaces should be washed with Gjøco Husvask or Gjøco Interiørrens and rinsed with water. Follow the instructions on the packaging. MFD, building boards, hard substrates, old semi-gloss or glossy paint should be mattified with sandpaper and dusted off. All surfaces should be primed with 1 coat of Gjøco Sperregrunn. When building with fibreglass, it may be necessary to sand the surface after priming to obtain a fine and smooth surface. Substrates treated with alkyd paint should always be primed before applying Gjøco Fashion.  New, fresh panels and old discoloured/yellowed panels should be primed with 1-2 coats of Gjøco Kvist og Sperregrunn or Gjøco Sperregrunn. |  |  |  |  |
| Directions for use | Gjøco Fashion is ready to use and should not normally be thinned. On interior details and surfaces where a smooth and even finish is desired, the use of a good quality brush is recommended. Apply evenly and generously.  On absorbent and porous surfaces, 3 coats are recommended to avoid streaks.  |  |  |  |  |
| Color              | Use the same batch number on the same coat and the same surface, to avoid gloss and color differences. Alternatively, different batch numbers can be mixed before use. Buckets where the color is mixed on different mixing machines and/or at different times can result in shade differences. Be aware of this if more paint is needed for the same project afterwards.  |  |  |  |  |
| Storage            | Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.  |  |  |  |  |
| Ecolabelling       | Gjøco Fashion is approved by Ecolabel Norway and meets the requirements for the Nordic Ecolabel Svanen.  The product has been tested in accordance with the test requirements set by BREEAM-NOR (2016). The product meets BREEAM-NOR HEA 02. Gjøco Silkematt Rom does not contain any substances on the A20 list.  |  |  |  |  |
| Disposal of waste  | Liquid paint must not be emptied into sewers or into nature, but delivered to an environmental station. Empty, clean, and dry plastic packaging without a handle can be delivered as plastic waste.  |  |  |  |  |
| Other information  | The application temperature in the air and the substrate must be at least +10 °C. Best results are achieved when applied at room temperature. It is also an advantage that the paint is at room temperature. Stir well before use. Painted surfaces must cure for at least 4 weeks before cleaning with a mild detergent. To avoid cracking along the panel joints as a result of changes in humidity, it is recommended that the panel boards are treated before installation. Alternatively, the panel can be treated in the late winter when the humidity is usually at its lowest. Packaging sizes: 0.68 and 2.7 liters  |  |  |  |  |

| Safety | See separate safety data sheet. Read the information on the packaging.             |  |  |
|--------|--|--|--|
|        | EU limit value for this product (cat. A/d): 130 g/l (2010). This product contains: |  |  |
|        | <75 g/I VOC.   |  |  |

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information Gjøco AS

Ørvegen 1160, 6639 Torvikbukt Telephone: +47 712 91 700 E-mail: office@gjoco.no

