

## Product datasheet

# Herregård Treolje XO



Herregård Treolje XO is an impregnating high-quality wood oil with added film preservative against black fungus. Prevents graying and cracking of impregnated wood. Herregård Treolje XO is used on outdoor terraces, retaining walls, garden furniture, etc. made of pressure-impregnated material. On light-colored wood, pigmented oil should be used for better protection.

Revised 06.12.2024

Symbols




### Technical data

Type:	Alkyd oil-based wood oil
Color:	Golden and clear
Flash point:	Approx. 62 °C
Specific gravity:	0.85 kg/l
Solid content:	Approx. 36 volum%
Application method:	Brush or roller.
Thinner / cleaning agent:	White Spirit
Recommended spreading rate:	Approx. 8-10 m <sup>2</sup> /liter, planed wood.
Drying time (23 °C, 50 % R.H.):	Depends on temperature, humidity, wind and film thickness.
Dust dry:	24 hours
Minimum application temperature:	+5 °C. Low temperatures result in longer drying time.

### Pretreatment

The substrate must be clean and dry. New, impregnated wood must be dry before treatment; this can take anywhere from a few weeks to 2-3 months. Rinse and brush off any impregnation residue. Clean the terrace with Gjøco Terrasserens. Follow the instructions on the packaging. Let dry thoroughly before further treatment. The terrace should be treated as soon as possible after it is clean and dry, to avoid the surface from wearing away due to weather exposure.

When treating old/previously treated wood, clean the terrace with Gjøco Terrasserens Gel. Follow the instructions on the packaging. Repeat the treatment if the substrate is very dirty. Let dry thoroughly before further treatment. Loose stain must be removed and gray, weathered surfaces must be wire-brushed or sanded down to fresh wood before further treatment. Loose flakes and wood fibers/gray wood can prevent penetration and cause peeling.

<b>Directions for use</b>	The substrate must be clean and dry before application. Stir Herregård Treolje XO well before use. On new wood, apply 1-2 coats wet-on-wet as needed. On previously treated wood, apply 1-2 coats as needed. The wood oil should penetrate the wood without forming a film. Film formation can lead to peeling. Wipe off excess oil with a lint-free cloth in the lengthwise direction.
<b>Storage</b>	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
<b>Disposal of waste</b>	Liquid stain must not be emptied into sewers or into nature, but must be delivered to an approved hazardous waste collection point. Empty, clean and dry packaging is delivered to approved reception. 
<b>Other information</b>	There are many different types of impregnated material. Check with the supplier when they recommend that the material be treated for the first time. Package sizes: 3 liters.
<b>Safety</b>	See separate safety data sheet. Read the information on the packaging. EU limit value for this product (kat. A/f): 700 g/l (2010). This product contains: <600 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information**  
**Gjøco AS**  
 Ørvegen 1160, 6639 Torvikbuk  
 Telephone: +47 712 91 700  
 E-mail: office@gjoco.no

