

Product datasheet

Gjøco Interiørbeis



Gjøco Interiørbeis is a water-thinned oil stain for indoor use on untreated pine and spruce wood. Can be used on wood panels, moldings, frames, furniture, doors, floors and ceilings.

Gives the wood a transparent and matte appearance. Can be mixed in many different stain colors. Not suitable for hard wood substrates that prevent the penetration of stain such as oak and parquet.

Revised 03.12.2024

Symbols



Technical data



Type:	Alkyd oil diluted in water
Color:	Clear/C-base, mixed in different colors.
Gloss:	Matte
Viscosity:	50-70 s, F4
Specific gravity:	Ca. 1 kg/l
Solid content:	Ca. 20 volum%
Application method:	Brush (full/oval intended for primer/stain)
Thinner/ cleaning agent:	Water
Recommended spreading rate:	14-17 m ² /litre
Drying times (23 °C, 50 % R.H.):	
Dry to use:	2 hours
Interval between coats:	24 hours. Full adhesion is achieved after 4 weeks of thorough curing. Varies with changes in temperature, humidity, ventilation and film thickness.
Minimum application temperature:	+10 °C. Best results are achieved when applied at room temperature.

Pretreatment

The substrate must be clean, dry and firm. Clean with Gjøco Gulvrens for floors and panels. Let the wood dry, and remove any raised fibers with light sandpaper. Remove sanding dust carefully with a broom or microfiber cloth. Previously treated substrates must be sanded down to bare wood. If you are unsure whether the wood has been treated, you should do a test coat on a small, inconspicuous area. In any case, a test coat should be done on old panels/wood.

Directions for use

Gjøco Interiørbeis should be applied in thin coats. If a transparent and less opaque surface is desired, wipe off excess stain with a sponge or lint-free cloth.

	<p>When applying more than one coat, the color will be more opaque and the drying time will be significantly longer between coats. It is recommended that test coats be applied to check that the color and result are as desired. When used on surfaces that are exposed to wear and tear, such as floors, tables and furniture, a final treatment with varnish or oil as a top coat is recommended. Allow a minimum of 24 hours before repainting.</p> <p>Treat 1–2 panel boards at a time along the entire length to avoid joints/splatters. To obtain a smooth and natural surface, excess stain can be wiped off immediately in the longitudinal direction with a lint-free cloth or sponge. It is recommended to clean the brush in water occasionally for larger jobs, to prevent the stain from drying and graining in the brush.</p>
Color	Use the same batch number on the same coat and the same surface, to avoid gloss and color differences. Alternatively, different batch numbers can be mixed before use. Buckets where the color is mixed on different mixing machines and/or at different times can result in shade differences. Be aware of this if more paint is needed for the same project afterwards.
Storage	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
Ecolabeling	<p>Gjøco Interiørbeis is approved by Ecolabel Norway and meets the requirements for the Nordic ecolabel Svanen.</p> 
Disposal of waste	<p>Liquid paint must not be emptied into sewers or into nature, but delivered to an environmental station. Empty, clean, and dry plastic packaging without a handle can be delivered as plastic waste.</p> 
Other information	<p>Stir well before use. Use good quality brushes intended for water-based products. To avoid cracking along the panel joints due to changes in humidity, it is recommended that the panel boards are treated before installation. Alternatively, the panel can be treated in the late winter when the humidity is normally at its lowest.</p> <p>Package size: 0.68 and 2.7 liters</p>
Safety	<p>See separate safety data sheet. Read the information on the packaging.</p> <p>EU limit value for this product (cat. A/e): 130 g/l (2010). This product contains: <70 g/l VOC.</p>

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information **Gjøco AS**
 Ørvegen 1160, 6639 Torvikbukta
 Telephone: +47 712 91 700
 E-mail: office@gjoco.no

