

## Product datasheet

# Gjøco Klarlakk Vanntynnbar



Gjøco Klarlakk vanntynnbar is a fast-drying and durable water-thinnable polyurethane varnish with a light filter. Intended for indoor use on wood such as parquet, wooden floors, stairs and railings.

Revised 03.12.2024

Symbols




### Technical data

Type:	Modified polyurethane/acrylic varnish
Color:	Clear
Gloss:	Ultra-matte 4-6, silk matt 15-20, semi-gloss 40-50, glossy 80-90
Specific gravity:	1.05 kg/l
Solid content:	35 volum%
Application method:	Paint brush or roller
Thinner/ cleaning agent:	Water
Recommended film thickness, wet:	100-150 micrometer
Recommended film thickness, dry:	43-65 micrometer
Recommended spreading rate:	10-15 m <sup>2</sup> /litre, depending on the substrate.
Drying times (23 °C, 50 % R.H.):	
Dry to use:	1 hours
Interval between coats:	Ca. 4 hours. Full adhesion is achieved after 4 weeks of thorough curing. Varies with changes in temperature, humidity, ventilation and film thickness.
Dry to use:	Ca. 8 hours
Minimum application temperature:	+5 °C. Best results are achieved at room temperature.

### Pretreatment

The substrate is first washed with Gjøco Floor and Panel Cleaner to remove grease, soap residue and wax. Follow the instructions on the packaging. Previously varnished surfaces and parquet varnished from the factory should be matt sanded with sandpaper 150-180. Using a sander ensures even and thorough sanding. Vacuum and dry with a lint-free, slightly damp cloth. On previously varnished/oiled surfaces, adhesion should be tested before application.

<b>Directions for use</b>	Mix the contents of packages with different batch numbers before use. Always use the same batch number on the same surface. Stir well before and during use. Apply the varnish quickly and evenly in the lengthwise direction of the wood. Apply a minimum of 3 coats to new wood. A minimum of 2 coats is recommended on previously varnished surfaces. Any raised fibres are sanded away with fine sandpaper. Remove sanding dust carefully. Light matt sanding is recommended between each coat to ensure good adhesion.
<b>Maintenance and cleaning</b>	Avoid exposing the paintwork to stress such as water spills, heavy furniture, carpets for the first two weeks after painting. Also avoid washing for the first 14 days. Use dry cleaning methods such as dry mopping and vacuuming for regular cleaning. It is recommended to use as little water as possible. The pH value of the washing water should not exceed 9, and the temperature should be lower than +40 °C. It is recommended to place mats at entrance doors to protect the floor. It is recommended that water spills, etc. are wiped up immediately to avoid marks.
<b>Storage</b>	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
<b>Disposal of waste</b>	Liquid paint and washing water should not be emptied into sewers or into nature, but delivered to an approved hazardous waste collection point. Empty, clean and dry plastic packaging without handles can be delivered as plastic waste.
	
<b>Other information</b>	Different batch numbers are mixed before use to avoid gloss differences. It is recommended to apply a test coat, as the colour of the substrate will affect the final result. Package size: 0.75 and 3 litres
<b>Safety</b>	See separate safety data sheet. Read the information on the packaging. EU limit value for this product (cat. A/i): 140 g/l (2010). This product contains: <80 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information**  
**Gjøco AS**  
 Ørvegen 1160, 6639 Torvikbukta  
 Telephone: +47 712 91 700  
 E-mail: office@gjoco.no

