

Product datasheet

Gjøco Oljedekkbeis



Gjøco Oljedekkbeis is a thixotropic alkyd oil-based top stain with added film-protecting antifungal agent. Has good application properties and provides a subdued wood structure. Gjøco Oljedekkbeis is used on new and primed, previously stained, or top-stained wood. Can also be used on pressure-impregnated, primed material.

Revised 10.12.2024

Symbols



Technical data

Type:	Alkyd oil-based deck stain
Color:	White, A, B, C, ochre and oxide red base that is refracted over Gjøcomix.
Gloss:	Semi gloss
Flash point:	>60 °C
Specific gravity:	1.16 kg/l
Solid content:	Approx. 51 volum%
Application method:	Brush or roller. Spraying is recommended by professionals
Thinner / cleaning agent:	White Spirit
Film thickness, wet:	80-100 mikrometers
Film thickness, dry:	35-45 mikrometers
Recommended spreading rate:	8-10 m ² /liter, depending on the substrate.
Guiding data for airless spray:	
Nozzle:	0,015"-0,018"
Spray angel:	65°-80°
Pressure at nozzle:	150 kg/cm ²
Drying time (23 °C, 50 % R.H.):	Depends on temperature, humidity, wind and film thickness.
Dust dry:	8 hours
Interval between coats, minimum:	24 hours

Pretreatment

The surface must be clean and dry before painting begins. New wood that has been untreated for more than 4 weeks should be wire-brushed before treatment with Gjøco Oljegrunding. Dirty surfaces should be

cleaned with Gjøco Husvask. New and bare wood, including pressure-impregnated wood, should be treated with 1 coat of Gjøco Oljegrunning. All end wood must be well saturated with Gjøco Oljegrunning, 3-4 coats wet-on-wet. On planed wood, sharp edges and other shiny surfaces, wire-brushing/sanding may be necessary to ensure adhesion and good edge coverage.

On previously treated wood, grease and other contaminants should be removed with Gjøco Kraftvask. Previously painted or top-stained wood should be brushed clean of loose stain and wood fibers with a wire brush/sanding. Bare wood should be primed with Gjøco Oljegrunning, and stained with Gjøco Oljedekkbeis. All end wood must be well saturated with Gjøco Oljegrunning, 3-4 coats wet-on-wet.

Directions for use

Gjøco Oljedekkbeis is ready to use and should not normally be thinned. Apply 2 coats to new unplaned wood and 3 coats to new planed wood. Apply 1-2 coats to previously stained, top-stained or painted wood as needed, or 3 coats to planed wood. Ensure that all end wood is sufficiently saturated (3-4 coats).

Color

Use the same batch number on the same coat and the same surface to avoid gloss and color differences. Buckets where the color is mixed on different mixing machines and/or at different times can result in shade differences. Be aware of this if more paint is needed for the same project later.

Storage

Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.

Disposal of waste

Liquid stain should not be emptied into sewers or into the environment, but delivered to an approved hazardous waste collection point. Empty, clean and dry packaging should be delivered to an approved collection point.


Other information

Any oil float-up should be stirred in well for a while before use. The contents of cans with different production numbers should be mixed before use to avoid differences in gloss and color. Dew on a semi-dry surface can cause dull streaks. Dull streaks can also occur when drying at low temperatures and high humidity. Sun on a wet or semi-dry surface can cause blistering. Avoid applying in sunlight. Painting on fire-protected cladding can cause flaking/salt precipitation. Substrates that have previously been treated with linseed oil or pure linseed oil stain must be cleaned to bare wood to prevent later blistering. Previous tar treatment can cause discoloration. Take a test coat. Dark, sharp and bright colors will be more susceptible to fading on weathered walls than light colors.
Packaging sizes: 0.68; 2.7 and 9 liters.

Safety

See separate safety data sheet. Read the information on the packaging.
EU limit value for this product (kat. A/e): 400 g/l (2010). This product contains: <400 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information

Gjøco AS

Ørvegen 1160, 6639 Torvikbukt

Telephone: +47 712 91 700

E-mail: office@gjoco.no

