

Product Data Sheet

Gjøco Oljegrunning



Gjøco Oljegrunning is a light thixotropic primer for exterior wood and is based on penetrating alkyds and oils. Contains film preservative against black fungus. Gjøco Oljegrunning is ideal for priming bare exterior wood of spruce and pine. Can also be used on impregnated wood.

Revised 10.04.2026

Symbols




Technical data

| | |
|----------------------------------|--|
| Type: | Primer based on alkyd oils |
| Color: | Clear and white |
| Flash point: | >62 °C |
| Specific gravity: | 0.89 kg/l |
| Solid content: | Approx. 42 volum% |
| Application method: | Brush. Do not spray. |
| Thinner / cleaning agent: | White Spirit |
| Film thickness, wet: | 80mikrometers |
| Film thickness, dry: | 20 mikrometers |
| Recommended spreading rate: | |
| Planed wood: | 6-10 m ² /liter |
| Unplaned wood: | 4-8 m ² /liter |
| Drying time (23 °C, 50 % R.H.): | Depends on temperature, humidity, wind and film thickness. |
| Dust dry: | 2 hours |
| Interval between coats, minimum: | 24 hours |
| Minimum application temperature: | Can be used below +5 °C, but the substrate must be dry and frost-free. Low temperatures will significantly extend the drying time. |

Pretreatment

The substrate must be clean and dry. New wood that has been untreated for more than 4 weeks must be wire brushed before applying Gjøco Oljegrunning. Vacuum-impregnated windows must be degreased before priming. Round off sharp edges to achieve the best possible edge coverage. Smooth and hard surfaces such as planed wood can be lightly sanded before priming. Previously painted wood must be scraped clean of loose paint, and weathered surfaces must be wire brushed

| | |
|---------------------------|--|
| | down to fresh wood. Grease and other contaminants must be removed with Gjøco Husvask. |
| Directions for use | The product is ready to use and should not be thinned. New and untreated wood should be treated with Gjøco Oljegrunning as soon as possible after installation. Bare wood should be given one coat. Use a wide brush. Remember to saturate end wood and joints with 3-4 coats. Further treatment should be carried out as soon as possible and within 1 month. Gjøco Oljegrunning should not form a film; any excess should be wiped off with a lint-free cloth. |
| Storage | Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free. |
| Eco-labeling | BREEAM-NOR v6.1 – MAT02: Contains no substances listed under REACH Article 59(10) – the Candidate List and the Norwegian A20 list. See also the product safety data sheet. |
| Disposal of waste | Liquid stain should not be emptied into sewers or into the environment, but delivered to an approved hazardous waste collection point. Empty, clean and dry packaging should be delivered to an approved collection point.  |
| Other information | Any oil that has risen in the can should be stirred in for a while before use. Clear oil primer is recommended under transparent stain, because pigmented oil primer can cause color changes. Feel free to do a test coat. Packaging sizes: 0.75; 3 and 10 liters. |
| Safety | See separate safety data sheet. Read the information on the packaging. EU limit value for this product (kat. A/h): 700 g/l (2010). This product contains: <500 g/l VOC. |

The information provided in this data sheet is based on laboratory tests and practical experience. As the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the quality of the product itself. The products are supplied in accordance with our general terms and conditions of sale, delivery, and service, unless otherwise agreed in writing. We reserve the right to change the stated data without prior notice. Paint may be regarded as a semi-finished product, and the final result depends on factors such as surface preparation, temperature, application method, type of substrate, etc.

Contact information **Gjøco AS**
Ørvegen 1160, 6639 Torvikbukt, Norway
Telephone: +47 712 91 700
E-mail: office@gjoco.no

