

# Product datasheet

## Gjøco Superfinish 40



Gjøco Superfinish 40 is a silky matt, pure acrylic paint for indoor use. It has good application properties and provides good flow. Used for intermediate and top coats on doors, windows, frames, moldings, panels and furnishings.

Revised



07.10.2025

Symbols



### Technical data

Type:	Water-thinnable pure acrylic paint
Color:	White, A, B and C base, colors are mixed over Gjøcomix.
Gloss:	Semi-gloss 40
Viscosity:	80-100 P
Specific gravity:	Ca. 1.1 – 1.3 kg/l
Solid content:	34 – 36 volum%
Application method:	Brush or roller. Spraying should be done by professionals.
Thinner/ cleaning agent:	Water
Recommended spreading rate:	Min. 8 – 10 m <sup>2</sup> /litre
Recommended data for airless spray:	
Nozzle tip:	0.20–0.36 mm (0.008–0.014")
Spray angle degrees:	50°–80°
Pressure at nozzle:	15 MPa (150 kg/cm <sup>2</sup> )
	The choice of nozzle, fan angle, and pressure must be adjusted to the specific spray equipment and substrate.
Drying times (23 °C, 50 % R.H.):	
Dry to use:	1 hours
Interval between coats:	4 hours
Dry to use:	24 hours. Full adhesion is achieved after 4 weeks of curing. Varies with changes in temperature, humidity, ventilation and film thickness.
Minimum application temperature:	+10 °C. Best results are achieved when applied at room temperature.

<b>Pretreatment</b>	<p>The substrate must be clean and dry. Previously painted surfaces can be washed with Gjøco Husvask and rinsed with water. Old glossy and semi-gloss paint can be mattified with sandpaper.</p> <p>Untreated panel: Prime with a minimum of 2 coats of Gjøco Sperregrunn.</p> <p>Previously painted substrate: Prime with 1 coat of Gjøco Sperregrunn. Substrates treated with alkyd paint should always be primed before applying Gjøco Superfinish 40.</p>
<b>Directions for use</b>	Gjøco Superfinish 40 is ready to use and should not normally be thinned. Apply generously and evenly with suitable painting tools. On absorbent and porous surfaces, 3 coats are recommended to avoid streaks. To achieve satisfactory flow, one should avoid going back to semi-dry paint.
<b>Storage</b>	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
<b>Ecolabelling</b>	<p>Gjøco Superfinish 40 is approved by Ecolabel Norway and meets the requirements for the Nordic Ecolabel Svanen.</p> 
<b>Disposal of waste</b>	<p>Liquid paint must not be emptied into sewers or into nature, but delivered to an environmental station. Empty, clean, and dry plastic packaging without a handle can be delivered as plastic waste.</p> 
<b>Other information</b>	<p>Application temperature in air and substrate must be at least +10 °C. Painted surfaces must cure for a minimum of 4 weeks before cleaning with a mild detergent.</p> <p>Stir well before use. Different production numbers are mixed before use.</p> <p>Package sizes: 0.68 and 2.7 liters</p>
<b>Safety</b>	<p>See separate safety data sheet. Read the information on the packaging.</p> <p>EU limit value for this product (cat. A/d): 130 g/l (2010). This product contains: &lt;75 g/l VOC.</p>

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information**

**Gjøco AS**  
 Ørvegen 1160, 6639 Torvikbukt  
 Telephone: +47 712 91 700  
 E-mail: office@gjoco.no

