

Product datasheet

Gjøco Supermatt Rom 01



Gjøco Supermatt Rom 01 is a water-thinnable, full-matt acrylic wall paint that provides color depth and a beautiful, calm result without glare. Used on walls made of, for example, building boards, paintable wallpaper, plaster, concrete and sand filler.

Revised 26.11.2024

Symbols





Technical data

Type:	Pure acrylic paint
Color:	White, A, B and C base, colors are mixed over Gjøcomix.
Gloss:	Flat 01
Viscosity:	70-90 P
Specific gravity:	1.3 kg/l
Solid content:	Ca. 40 volum%
Application method:	Brush, roller, or spray. Spraying should be done by professionals.
Thinner/ cleaning agent:	Water
Recommended spreading rate:	8 - 10 m ² /litre, depending on the substrate.
Drying times (23 °C, 50 % R.H.):	
Dry to use:	1 hours
Interval between coats:	2 hours. Full adhesion is achieved after 4 weeks of curing. Varies with changes in temperature, humidity, ventilation and film thickness.
Minimum application temperature:	+10 °C. Best results are achieved when applied at room temperature.

Pretreatment

The substrate must be clean and dry. Clean with Gjøco Husvask or a suitable cleaning agent and wash with clean water. Old, glossy and semi-gloss paint should be mattified with sandpaper and dusted off. Substrates painted with alkyd paint should always be primed before applying Gjøco Supermatt Rom. Surfaces discoloured by nicotine, soot and various dyes should be applied with at least one coat of Gjøco Sperregrunn.

Directions for use	Gjøco Supermatt Rom is ready to use and should not normally be thinned. Apply evenly and generously. On absorbent and porous surfaces, 3 coats are recommended to avoid streaks. It is advisable to use a roller with an extension handle because it is easier to avoid streaks. To get an even result, it is recommended to roll entire lengths in the same direction on the entire wall.
Color	Use the same batch number on the same coat and the same surface, to avoid gloss and color differences. Alternatively, different batch numbers can be mixed before use. Buckets where the color is mixed on different mixing machines and/or at different times can result in shade differences. Be aware of this if more paint is needed for the same project afterwards.
Storage	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
Ecolabelling	Gjøco Supermatt Rom is approved by Ecolabel Norway and meets the requirements for the Nordic Ecolabel Svanen. 
Disposal of waste	Liquid oil must not be emptied into sewers or into nature, but delivered to an environmental station. Empty, clean, and dry plastic packaging without a handle can be delivered as plastic waste. 
Other information	Application temperature in air and substrate must be at least +10 °C. Painted surfaces must cure for a minimum of 4 weeks before cleaning with a mild detergent. Light marks on dark surfaces can be removed with a microfibre cloth and clean water. Stir well before use. Packaging size: 0.68; 2.7 and 9 liters
Safety	See separate safety data sheet. Read the information on the packaging. EU limit value for this product (cat. A/a): 30 g/l (2010). This product contains: <1 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information
Gjøco AS
 Ørvegen 1160, 6639 Torvikbukt
 Telephone: +47 712 91 700
 E-mail: office@gjoco.no

