

Product datasheet

Gjøco Dekksolje



Gjøco Dekksolje is an impregnating oil based on pure wood tar, turpentine, alkyds and a film preservative against black fungus intended for wooden boats and docks.

Revised 11.12.2024

Symbols



Technical data

Type:	Tar-based wood impregnation
Color:	Light brown-golden
Flash point:	Approx. 40 °C
Specific gravity:	0.86 kg/l
Solid content:	Approx. 40 volum%
Application method:	Brush
Thinner / cleaning agent:	White spirit or turpentine.
Recommended spreading rate:	Approx. 5 m ² /liter, depending on surface.
Drying time (23 °C, 50 % R.H.):	
Dust dry:	8-10 hours
Overpainting interval, minimum:	Apply wet-on-wet until the substrate is saturated.
Min. application temperature:	+10 °C, lower temperatures extend drying time significantly.

Pretreatment

The substrate must be clean and dry. Grease and contamination must be removed with Gjøco Husvask. Previously treated wood must be scraped clean of loose oil and weathered surfaces must be wire brushed down to fresh wood. Surfaces affected by fungus and green rot must be treated with Gjøco Sopp- og grønskefjerner. Allow to dry before further treatment.

Directions for use

Stir well before use. New or absorbent wood is treated wet-on-wet with Gjøco Dekksolje diluted with 30-50% turpentine. Then apply 2-3 coats of pure Gjøco Dekksolje. Gjøco Dekksolje contains tar, and repeated treatments will therefore darken the wood.

Storage

Close the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.

Disposal of waste

Liquid oil and washing water must not be emptied into sewers or into nature, but must be delivered to an environmental station.



Other information

The product must be stored in accordance with national regulations. The packaging must be kept tightly closed and stored dry at a constant temperature. Packaging sizes: 0.75; 3; 10 and 200 liters.

Safety

See separate safety data sheet. Read the information on the packaging.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information

Gjøco AS
Ørvegen 1160, 6639 Torvikbuk
Telephone: +47 712 91 700
E-mail: office@gjoco.no

