

## Product datasheet

# Gjøco Emaljelakk



Gjøco Emaljelakk is a glossy and durable topcoat intended for exterior primed surfaces of metal, wood and hard plastic. Used on agricultural implements, iron structures, machinery, gate posts, fences, wrought iron gates, bicycles, garden furniture, furniture, furnishings, lamps, pots, candlesticks, flagpoles, etc. Also suitable for use on wooden details on boats above the waterline.

Revised 06.03.2025

Symbols




### Technical data

Type:	Alkyd oil-based paint
Color:	Different
Gloss:	Gloss
Specific gravity:	1.1 kg/l
Solid content:	Approx. 54 volum%
Application method:	Brush, roller or high-pressure spray.
Thinner / cleaning agent:	White Spirit
Recommended spreading rate:	Approx. 10-12 m <sup>2</sup> /liter, depending on surface.
Recommended film thickness, wet:	90 micrometers
Recommended film thickness, dry:	40 micrometers
Guiding data for airless spray:	
Nozzle:	0,015-0,021"
Spray angel:	65-80°
Pressure at nozzle:	150 kg/cm <sup>2</sup>
Drying time (23 °C, 50 % R.H.):	
Dust dry:	Approx. 5 hours
Interval between coats:	24 hours

### Pretreatment

The substrate must be free of grease, oil and other contaminants. Clean with Gjøco Kraftvask or Gjøco Husvask. Follow the instructions on the packaging. Remove old loose paint and loose rust. Prime iron and steel with Gjøco Antirustprimer. Prime aluminum, zinc, sandblasted/galvanized steel with Gjøco Metallgruning.

<b>Directions for use</b>	Stir the paint well before use. The paint is ready to use and should not be thinned. Apply 2-3 coats as needed.
<b>Storage</b>	Close the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
<b>Disposal of waste</b>	Liquid paint and washing water must not be emptied into sewers or into nature, but must be delivered to an environmental station. 
<b>Other information</b>	The product must be stored in accordance with national regulations. The packaging must be kept tightly closed and stored dry at a constant temperature. Packaging sizes: 0.68; 2.7 and 9 liters.
<b>Safety</b>	See separate safety data sheet. Read the information on the packaging.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information** **Gjøco AS**  
 Ørvegen 1160, 6639 Torvikbukt, Norway  
 Telephone: +47 712 91 700  
 E-mail: office@gjoco.no

