

Product datasheet

Herregård Exclusive Oljedekkbeis



Herregård Exclusive Oil Deck Stain is a durable and weather-resistant deck stain for outdoor use on exterior panels. It is particularly suitable for locations exposed to the weather. Contains UV filters that prevent fading and dulling, and film preservatives that prevent the growth of black mold and algae. Can be used on bare, new, primed and previously stained surfaces. Herregård Exclusive Oil Deck Stain can be used without primer.


Revised 05.12.2024

Symbols



Technical data

Type:	Alkyd oil-based deck stain
Color:	White, A, B, C, yellow, bright red, ochre and oxide red base
Gloss:	20 – 40 semi gloss
Flash point:	>60 °C
Specific gravity:	1.17 kg/l
Solid content:	Approx. 60 volum%
Application method:	Brush or roller. Spraying is recommended by professionals
Thinner / cleaning agent:	White Spirit
Film thickness, wet:	100 mikrometers
Film thickness, dry:	50 mikrometers
Recommended spreading rate:	
Planed wood:	10-16 m ² /liter
Unplaned wood:	5-8 m ² /liter
Guiding data for airless spray:	
Nozzle:	0,015"-0,018"
Spray angel:	65°-80°
Pressure at nozzle:	150 kg/cm ²
Drying time (23 °C, 50 % R.H.):	Depends on temperature, humidity, wind and film thickness.
Dust dry:	6 hours
Interval between coats, minimum:	24 hours
Minimum application temperature:	-5 °C. Low temperatures result in longer drying time, and increased the risk of dew matting etc.

Pretreatment	<p>The substrate must be clean and dry before painting begins. New wood must be treated before or as soon as possible after construction. Planed wood must be roughened/sanded before application. New wood that has been untreated for more than 4 weeks must be cleaned and wire brushed before further treatment. Previously treated surfaces must be washed with Gjøco Kraftvask. Loose paint must be removed and loose wood fibers must be removed with a wire brush/sanding. On pressure-impregnated wood, salt deposits must be removed. It is not necessary to prime bare wood, but if desired and for extra protection it can be primed with Gjøco Oljegrunning. On planed timber, wood/folds, sharp edges and other shiny surfaces, wire brushing/sanding may be necessary to ensure adhesion and good edge coverage.</p>
Directions for use	<p>Herregård Exclusive Oljedekkbeis is ready to use and should not normally be thinned. It is important to apply sufficient cover stain to ensure long durability. New unplanned wood should be applied with a minimum of 2 coats and new planed wood/foldings/details should be applied with a minimum of 3 coats. Previously stained, cover stained or painted wood should be applied with 1-2 coats as needed, or 3 coats on planed wood. Ensure that end timbers and cut surfaces are sufficiently saturated (3-4 coats). Herregård Exclusive Oljedekkbeis can be used at sub-zero temperatures, but should not be used on frosted surfaces.</p>
Color	<p>Use the same batch number on the same coat and the same surface to avoid gloss and color differences. Buckets where the color is mixed on different mixing machines and/or at different times can result in shade differences. Be aware of this if more paint is needed for the same project later.</p>
Storage	<p>Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.</p>
Disposal of waste	<p>Liquid paint should not be emptied into sewers or into nature, but delivered to an approved hazardous waste collection point. Empty, clean and dry plastic packaging without handles can be delivered as plastic waste. Empty tin cans should be delivered to an environmental waste station.</p>
	
Other information	<p>Any oil float-up should be stirred in well for a while before use. The contents of cans with different production numbers should be mixed before use to avoid differences in gloss and color. Dew on a semi-dry surface can cause dull streaks. Dull streaks can also occur when drying at low temperatures and high humidity. Sun on a wet or semi-dry surface can cause blistering. Therefore, avoid applying in sunlight. Painting on fire-protected cladding can cause flaking/salt precipitation. Substrates that have previously been treated with linseed oil or pure linseed oil stain must be cleaned to bare wood to prevent later blistering. Previous tar treatment can cause discoloration. Take a test coat. Packaging sizes: 2.7 and 9 liters.</p>
Safety	<p>See separate safety data sheet. Read the information on the packaging. EU limit value for this product (kat. A/e): 400 g/l (2010). This product contains: <400 g/l VOC.</p>

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information

Gjøco AS
Ørvegen 1160, 6639 Torvikbukt
Telephone: +47 712 91 700
E-mail: office@gjoco.no

