

Product datasheet

Herregård Exclusive Oljemaling



Herregård Exclusive Oljemaling is a durable and weather-resistant oil paint for exterior woodwork. It is particularly well suited for locations exposed to the weather, and provides good protection against fading and dulling. Herregård Exclusive Oljemaling is reinforced with extra film-protecting anti-fungal agent and UV protector. It has good adhesion to the substrate, and is suitable for doors and windows. Herregård Exclusive Oljemaling is used on new and primed wood, previously stained or painted externally planed or unplanned wood.

Revised


11.03.2025

Symbols



Technical data

Type:	Oil paint
Color:	White, A, B, C, yellow, clear, red, ocher and oxyd red base.
Gloss:	40 – 60 semi gloss
Flash point:	>60 °C
Specific gravity:	1.2 kg/l (base A)
Solid content:	Approx. 59 volum% (base A)
Application method:	Brush or roller. Spraying is recommended by professionals
Thinner / cleaning agent:	White Spirit
Film thickness, wet:	80-140 mikrometers
Film thickness, dry:	50-85 mikrometers
Recommended spreading rate:	
Planed wood:	10-15 m²/liter
Unplaned wood:	6-9 m²/liter
Guiding data for airless spray:	
Nozzle:	0.46 mm / 0,018"
Spray angel:	65°-80°
Pressure at nozzle:	150 kg/cm²
Drying time (23 °C, 50 % R.H.):	
Dust dry:	12 hours. Depends on temperature, humidity, wind and film thickness.
Interval between coats, minimum:	24 hours. Depends on temperature, humidity, wind and film thickness.
Minimum application temperature:	0 °C. Low temperatures result in longer drying time, and increased the risk of dew matting etc.

Pretreatment	<p>The surface must be clean and dry before painting begins.</p> <p>New wood that has been left untreated for more than 4 weeks is wire brushed before treatment with Gjøco Oljegrunning. Apply 1 coat of Gjøco Oljegrunning to new and bare wood, also pressure-treated. All endwood must be thoroughly saturated with Gjøco Oil Primer, 3-4 coats wet-on-wet. On planed wood, sharp edges and other shiny surfaces, steel brushing/grinding may be necessary to ensure adhesion and good edge coverage.</p> <p>Previously treated wood is treated with Gjøco Kraftvask to remove grease and other contaminants. Previously oil-stained or cover-stained wood is brushed clean of loose stain and wood fibers with a steel brush/grinding. Bare wood is primed with Gjøco Oljegrunning and stained with Herregård Exclusive Oljedekkbeis. All endwood must be thoroughly saturated with Gjøco Oljegrunning, 3-4 coats wet-on-wet.</p>
Directions for use	<p>Herregård Exclusive Oljemaling is ready for use and should not normally be thinned. Apply 2 coats to new unplanned wood and 3 coats to new planed wood. Previously stained, top-stained or painted wood, apply 1-2 coats as needed, possibly 3 coats on planed wood. Make sure all endwood is sufficiently saturated (3-4 coats).</p>
Storage	<p>Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.</p>
Disposal of waste	<p>Liquid paint must not be emptied into sewers or into nature, but must be delivered to an approved hazardous waste collection point. Empty, clean and dry packaging is delivered to approved reception.</p> 
Other information	<p>Any oil floating up should be stirred in well for a while before use. The contents of cans with different production numbers are mixed before use to avoid gloss and color differences. Dew on a semi-dry surface can produce dull shields. Matt shields can also occur when drying at low temperatures and high humidity. Sun on a wet or semi-dry surface can cause blistering. Dark colors that get a high temperature in the sun are more prone to sun blisters than light colors. Avoid application in sunlight. Paint on fire-protected cladding can cause flaking/salt precipitation. Dark, sharp and clear colors will be more prone to fading on the weather walls than light colors. Substrates that have previously been treated with linseed oil or pure linseed oil stain must be cleaned to bare wood to ensure against subsequent blistering. Previous tar treatment can cause discolouration. Take a test coat.</p> <p>Packaging sizes: 0.68, 2.7 and 9 litres.</p>
Safety	<p>See separate safety data sheet. Read the information on the packaging.</p> <p>EU limit value for this product (kat. A/d): 300 g/l (2010). This product contains: <300 g/l VOC.</p>

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information

Gjøco AS

Ørvegen 1160, 6639 Torvikbukt

Telephone: +47 712 91 700

E-mail: office@gjoco.no

