

Product datasheet

Herregård Extra



Herregård Extra is a water-repellent oil paint with good weather resistance for outdoor use. Contains a film preservative that prevents the growth of black mold and algae. Herregård Extra can be used on exterior new, old, stained, painted or pressure-impregnated wood. Can also be used as a topcoat on primed metal and plastic used on buildings. Herregård Extra should be used in a system with Gjøco Oljegrunning.

Revised


08.10.2025

Symbols



Technical data

Type:	Water-thinned hybrid paint based on alkyd and acrylic.
Color:	White, A, B, C and oxyd red base.
Gloss:	Semi-gloss 40
Viscosity:	130-150 P
Specific gravity:	Approx. 1.25 kg/l (base white)
Application method:	Brush or roller. Spraying is recommended by professionals.
Thinner / cleaning agent:	Water
Film thickness, wet:	90-130 mikrometers
Film thickness, dry:	40-55 mikrometers
Recommended spreading rate:	
Planed wood:	6-8 m ² /liter
Unplaned wood:	8-12 m ² /liter
Recommended data for airless spray:	
Nozzle tip:	0.46 mm (0.018")
Spray angle degrees:	65°-80°
Pressure at nozzle:	15-18 MPa (150-180 kg/cm ²)
	The choice of nozzle, fan angle, and pressure must be adjusted to the specific spray equipment and substrate.
Drying time (23 °C, 50 % R.H.):	Depends on temperature, humidity, wind and film thickness. Do not paint if there is a risk of dew or rain before the paint film is dry.
Dust dry:	3 hour
Interval between coats:	24 hours
Minimum application temperature:	+5 °C. Low temperatures result in longer drying time, and increased the risk of dew matting etc.

Pretreatment	The substrate must be clean and dry. New, fully primed, bare and pressure-impregnated wood must be applied with 1 coat of Gjøco Oljegrunning clear. New wood that has been untreated for more than 4 weeks must be cleaned and wire-brushed before treatment with Gjøco Oljegrunning. All end wood/cut surfaces must be well saturated with Gjøco Oljegrunning, 3-4 coats wet-on-wet. Previously treated substrates must be cleaned with Gjøco Kraftvask. Loose paint, stain and wood fibres must be removed by scraping/brushing. On planed wood, glossy and hard substrates, side edges and seams on outer panels, wire-brushing/sanding may be necessary to ensure adhesion. To achieve the best possible edge coverage, round off sharp edges before priming.
Priming	New and untreated bare wood must be applied with one coat of Gjøco Oljegrunning. For extra good protection ready primed timber from factory or impregnated wood, requires a thin coat of Gjøco Oljedekkbeis / Oljemaling in the same color as the desired top coat, before further treatment.
Directions for use	New unplaned wood should be treated with 2 coats and new planed wood with 3 coats. Previously treated wood should be treated with 1-2 coats as needed, or 3 coats on planed wood.
Color	Use the same batch number on the same coat and the same surface to avoid shade differences in the color. Buckets where the color is mixed on different mixing machines and/or at different times can give shade differences. Be aware of this if more paint is needed for the same project afterwards.
Storage	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
Disposal of waste	Liquid paint must not be emptied into sewers or into nature, but must be delivered to an approved hazardous waste collection point. Empty, clean and dry plastic packaging without handle, can delivered as plastic waste.
	
Other information	The substrate must be firm, clean and dry before applying the paint. Substrates previously treated with linseed oil paint/stain may blister. Previous tar treatment may cause discoloration, which is particularly visible on light colors. Dew on a semi-dry surface may cause dull spots. Sun on a wet or semi-dry surface may cause leather drying and blistering. Do not use on frosted wood. Painting on fire-protected cladding may cause salt precipitation and flaking. The product should not be thinned or mixed with foreign oils/products. Bases should be broken. Different batch numbers should be mixed before use. Application temperature in air and substrate must be at least +5 °C. Store dry and frost-free. For more detailed information, see safety and technical data sheet. Packaging sizes: 2.7 and 9 liters.
Safety	See separate safety data sheet. Read the information on the packaging. EU limit value for this product (kat. A/d): 130 g/l (2010). This product contains: <40 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information

Gjøco AS

Ørvegen 1160, 6639 Torvikbukt

Telephone: +47 712 91 700

E-mail: office@gjoco.no

