

## Product datasheet

# Gjøco Kalkmaling



Gjøco Kalkmaling is a mineral lime paint for interior use in dry rooms. Provides a vibrant and concrete-like surface. Used on building boards, plaster, concrete and filled surfaces. In areas with a risk of wear, moisture and water spills, application of Gjøco Sealer as a top coat is recommended.

Revised

03.07.2025

Symbols



### Technical data


Type:	Mineral lime paint
Color:	Bases mixed in different colors.
Gloss:	Fully matte 01
pH:	12-13
Application method:	Brush
Thinner/ cleaning agent:	Water. Paint should not normally be thinned.
Recommended spreading rate:	8-10 m <sup>2</sup> /litre, depending on the substrate.
Drying times (23 °C, 50 % R.H.):	
Dry to use:	1 hours
Interval between coats:	4 hours. The overpainting interval for using Gjøco Sealer is 24 hours.
Minimum application temperature:	+10 °C. Best results are achieved when applied at room temperature.
Safety:	The product has a high pH; wear protective gloves and goggles.

### Pretreatment

The substrate must be firm, clean and dry. Clean with Gjøco Husvask or Gjøco Interiørvask. Previously oil-painted surfaces, MDF boards and hard, smooth substrates should be mattified with sandpaper. On previously painted substrates, it is recommended to prime with Gjøco Silkematt Rom before applying Gjøco Kalkmaling. On absorbent substrates and filled surfaces, it is recommended to prime with two coats of Gjøco Silkematt Rom in the same color as the lime paint to obtain an even substrate. Gjøco Kalkmaling cannot be used directly on substrates painted with alkyd paints, so if you are unsure about the substrate, it is recommended to prime with at least one coat of Gjøco Silkematt Rom.

### Directions for use

Apply 1 coat of Gjøco Kalkmaling. The paint should be applied with a brush and should be stroked/cross-brushed to achieve a vibrant surface. One coat is usually

	<p>sufficient. Take a test coat if more than one coat is desired; coat no. 2 can give a different play of color. The width of the brush is important for the result; the narrower the brush, the more play of color. A 100 mm brush gives a nice result, but other sizes can also be used. Take a test coat. The paint should be applied thinly, as too thick coats can cause cracking.</p> <p>Gjøco Kalkmaling has limited washability and will change color in the event of moisture, grease and water spills. It is recommended to apply Gjøco Sealer on surfaces where there is a risk of wear, moisture and water spills. Gjøco Sealer will give a deeper color effect. Feel free to take a test coat.</p> <p>Gjøco Sealer should be applied evenly and rolled out well, to avoid roll stripes and overlap. Feel free to use the same technique as when applying Gjøco Lime Paint with random brushing/rolling. Using Sealer can make unevenness in the substrate more visible. It is therefore important that the substrate is even and uniform, in order to get a smooth and beautiful end result.</p>
<b>Color</b>	Use the same batch number on the same coat and surface to avoid differences in gloss and colour. Alternatively, different batch numbers can be mixed together before use. Buckets where the colour has been mixed using different tinting machines and/or at different times may result in slight colour variations. Be aware of this if additional paint is needed for the same project at a later stage.
<b>Storage</b>	Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free.
<b>Disposal of waste</b>	<p>The product is classified as hazardous waste and must be delivered to an approved hazardous waste collection point. The product must not be discharged into the environment, sewage or water. Empty and dry packaging must be delivered to an approved collection point.</p> <p>See also regulations for hazardous waste.</p> 
<b>Other information</b>	<p>Use the same batch number on the same surface to avoid gloss and color differences. Stir well before use. May etch glass and metal. Gjøco Kalkmaling is a diffusion-open paint with a high pigment content. Due to the nature of the paint, some colors may give higher viscosity. The color is darker when wet and will change during drying. Alkyd-based products should not be used together with Gjøco Kalkmaling, because it can cause discoloration and cracking.</p> <p>Packaging size: 0.68 and 2.7 liters</p>
<b>Safety</b>	<p>See separate safety data sheet. Read the information on the packaging.</p> <p>EU limit value for this product (cat. A/I): 200 g/l (2010). This product contains: &lt;30 g/l VOC.</p>

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

**Contact information** **Gjøco AS**  
Ørvegen 1160, 6639 Torvikbukt



---

Telephone: +47 712 91 700

E-mail: [office@gjoco.no](mailto:office@gjoco.no)

---