

Product datasheet

Gjøco Gulv 15 Vanntynnbar



Gjøco Gulv 15 is a water-thinnable floor paint based on polyurethane-modified alkyd. The paint has good application properties, good flow and is very durable. Used indoors on wood, parquet, laminate, floor coverings and concrete in dry rooms. Suitable for use on ceramic tiles. On newly poured floors and on stressed floor surfaces such as warehouse and industrial floors and garages, use Gjøco Poxydekk, Gjøco Poxydekk Ekstrem or GjøcoPoxy SL.

Revised


08.10.2025

Symbols



Technical data

| | |
|-------------------------------------|---|
| Type: | Water-thinnable oil paint based on polyurethane |
| Color: | White, A, B and C base, colors are mixed over Gjøcomix. |
| Gloss: | Eggshell 15 |
| Specific gravity: | Ca. 1.2 kg/l |
| Solid content: | 38 – 40 volum% |
| Application method: | Wide paint brush or felt roller. Spraying should be done by professionals. |
| Thinner/ cleaning agent: | Water |
| Recommended data for airless spray: | |
| Nozzle tip: | 0.43–0.53 mm (0.017–0.021") |
| Spray angle degrees: | 50°–80° |
| Pressure at nozzle: | Follow the pump manufacturer's recommendations. |
| | The choice of nozzle, fan angle, and pressure must be adjusted to the specific spray equipment and substrate. |
| Recommended spreading rate: | 6 – 8 m ² /litre |
| Drying times (23 °C, 50 % R.H.): | |
| Dry to use: | 2 hours |
| Interval between coats: | Min. 8 hours. Full adhesion is achieved after 4 weeks of thorough curing. Varies with changes in temperature, humidity, ventilation and film thickness. |
| Minimum application temperature: | +10 °C. Best results are achieved when applied at room temperature. |

| | |
|---------------------------|--|
| Pretreatment | <p>Wood/parquet/laminate: The substrate must be clean, dry and free of grease. Previously painted surfaces can be washed with Gjøco Floor and Panel Cleaner or a suitable cleaning agent, and rinsed with water. Old glossy and semi-gloss paint must be mattified with sandpaper. Untreated, sanded or worn wooden floors must first be treated with Gjøco Sperregrunn (see separate recommendations for this product). Then treat with 2-3 coats of Gulv 15 water-thinnable. Old laminate floors do not need a primer. New laminate floors may contain substances that make it difficult to overpaint, do a test coat.</p> <p>Ceramic tiles: The substrate must be clean, dry and free of grease. Clean with Gjøco Floor and Panel Cleaner or a suitable cleaning agent, and rinse with water. Smooth and hard tiles must be sanded lightly with fine sandpaper to ensure adhesion. The paint can be applied directly without the use of a primer. If priming is desired, Gjøco Sperregrunn is recommended.</p> <p>Concrete: Floor 15 water-thinnable is suitable as a paint for older untreated concrete floors and previously painted concrete floors in dry rooms without heavy loads. The substrate must be clean, dry and free of grease and oil residues, on previously painted surfaces, loose paint must be removed and cleaned with Gjøco Floor and Panel Cleaner or a suitable cleaning agent. Old glossy or semi-gloss paint must be mattified with sandpaper. Vacuum and wipe with a lint-free cloth, preferably microfiber. It is important to remove all sanding dust etc. to achieve good adhesion. Old untreated concrete floors should be sanded before application.</p> <p>For newly poured floors, warehouse floors, garages and other floors with heavy loads, Gjøco Poxydekk, Gjøco Poxydekk Ekstrem or GjøcoPoxy SL are recommended.</p> |
| Directions for use | Gjøco Gulv 15 water-thinnable is ready to use and should not normally be thinned. Stir well and apply 2-3 coats depending on the substrate. Apply evenly and generously. |
| Color | Use the same batch number on the same coat and the same surface, to avoid gloss and color differences. Alternatively, different batch numbers can be mixed before use. Buckets where the color is mixed on different mixing machines and/or at different times can result in shade differences. Be aware of this if more paint is needed for the same project afterwards. |
| Storage | Seal the lid tightly when storing paint to prevent spillage and drying. The paint must be transported and stored upright, dry and frost-free. |
| Disposal of waste | <p>Liquid paint must not be emptied into sewers or into nature, but delivered to an environmental station. Empty, clean, and dry plastic packaging without a handle can be delivered as plastic waste.</p> <div data-bbox="555 1756 804 1832">  </div> |
| Other information | Store dry and frost-free. Stir well before use. Mix different batch numbers to avoid gloss and color differences. Mortar (MS joint compound) and similar joint compounds for ship floors, etc. can affect the drying time of the paint. Take a test coat. Should not be used on linoleum flooring and old floor coverings. If necessary, take a test coat to check that the paint dries and the result is as expected. |

Packaging sizes: 0.68 and 2.7 liters

Safety

See separate safety data sheet. Read the information on the packaging.
EU limit value for this product (cat. A/i): 140 g/l (2010). This product contains:
<80 g/l VOC.

The information on this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished products and as the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are delivered in accordance with our general terms and conditions for sales, delivery and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to change the specified data without prior notice. This data sheet replaces previous editions.

Contact information

Gjøco AS
Ørvegen 1160, 6639 Torvikbukt
Telephone: +47 712 91 700
E-mail: office@gjoco.no

