



FDV - Management, Operation and Maintenance

GjøcoPoxy SL



GjøcoPoxy SL is a 3-component self-leveling epoxy coating for floors in industrial and commercial buildings. It is designed for use on concrete and mineral substrates that must withstand heavy chemical and mechanical stress. The substrate must be pre-treated and primed before further coating.

Revised

14.10.2025

Application Instructions	Substrate:	The substrate must be solid, clean, dry, free of dust and grease, and have a temperature of at least +12 °C for both substrate and air, and at least 3 °C above the current dew point.
	Application method:	Notched trowel, steel trowel, or leveling rake. A spiked roller can be used to remove air bubbles.
	Thinner:	The product must not be thinned.
	Storage:	Store in a dry, frost-free place.
	Indoor environment / emissions:	The product has low emissions.
Product Data Sheet and Safety Data Sheet	A product data sheet and safety data sheet (SDS) have been prepared for the product. See www.gjoco.no .	
Maintenance	Cleaning:	Before repainting, Gjøco Gulv og Panelrens is recommended. Follow the instructions on the product. Newly painted surfaces should not be washed until after 4 weeks. Use microfiber cloths with clean water or mild soapy water. The temperature of the wash water should not exceed +40 °C, and the pH should not exceed 9. The use of cleaning agents containing abrasives can damage the surface. Cleaning should be performed carefully to avoid streaks. Cleaning frequency should be determined as needed. The paint film will wear faster with frequent or heavy cleaning.
	Interval:	The coating is affected by mechanical stress and wears depending on the level of use. Maintenance intervals will therefore vary according to need.

Waste Management	Liquid epoxy must not be poured into drains or released into the environment but should be delivered to a recycling or waste collection station. Cured epoxy can be disposed of at waste collection stations as residual waste, but it is recommended to contact the local facility for specific guidance, as regulations may vary locally. 
Repairs / Damage	Repairs and damage should be remedied using the same type of product. If other products are used, it must be documented that they are of the same type as previously applied. When repairing damage, the work should be carried out so that it does not differ from previous treatments. For repainting or color changes, it is recommended to use the same product as before. Contact the supplier or painting company.
Treated Surface / Type of Substrate:	
Painted in Color:	Color Name:
	NCS:
Batch Number:	
Painting Work Performed By:	
Date:	
Signature:	

The information in this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished, and since the conditions under which they are used are often beyond our control, we can only guarantee the quality of the product itself. The products are supplied in accordance with our general terms of sale, delivery, and service, unless otherwise agreed in writing. We reserve the right to make minor product modifications and to change the specified data without prior notice. This data sheet replaces previous editions and is automatically void five years after the date of issue.

Contact Information	Gjøco AS, Galterud Sagmoen 100, NO-2223 Galterud, Norway Phone: +47 712 91 700 Email: office@gjoco.no	
----------------------------	---	---