

Product Data Sheet

GjøcoPur T



GjøcoPur T is a solvent-free, flexible 2-component PU coating in a system for floors with high wear, such as parking garages, warehouses, or production facilities. GjøcoPur T is intended for use as a topcoat and is available in several colors.

Concrete substrates must always be primed with a solvent-free epoxy primer, which is sanded, see the system description for GjøcoPark System, or the technical data sheet for GjøcoPoxy BP, GjøcoPoxy Universal (EKO), or GjøcoPoxy MF. The product can also be used on steel.

Revised:

19.02.2025

Symbols




Applications

Parking garages
Production halls
Warehouse halls
Industrial premises

Technical Data

Color:	Standard colors, special colors upon request
Mixing ratio:	12 kg part A and 3 kg part B
Density of part A + part B:	1.40 kg/L
Moisture tolerance:	The product must not be used on damp substrates or exposed to moisture during curing. The relative humidity in the room should be below 90%, both during application and curing time.
Application method:	Toothed trowel or leveling rake, back-rolled
Cleaning agent:	Xylene. Cured product can only be removed mechanically.
Thinning:	The product should not be thinned.
Recommended consumption:	Approx. 1.1 kg/m ² . Depending on the desired slip resistance.
Pot life:	30 minutes. Use immediately after mixing part A, part B, and part C.
Minimum application temperature:	From +12 °C to +30 °C for the substrate and air, at least 3 °C above the dew point.
Walkable:	24 hours at 20°C.
Overpaintable, interval:	Maximum 24 hours at 20°C.
Minimum application temp. (°C):	+12°C for substrate and air, and at least 3°C above the dew point. Lower temperatures extend curing time.
Curing time:	7 days.
Shelf life:	2 years in unopened packaging under normal storage temperatures.

Color and Gloss:	Always use the same batch number for the entire application to avoid differences in gloss and color.
Surface Preparation	The substrate must be firm, clean, dry, and free of grease. Maximum residual moisture in the substrate should be 5% (95 RH). Concrete quality should be at least C 25. The preparation of the concrete is done by grinding, milling, shot-blasting, or sandblasting. The surface should be vacuumed thoroughly at the end. The surface should be primed, for example, with GjøcoPoxy BP, GjøcoPoxy MF, or GjøcoPoxy Universal (EKO). Ensure that the primer covers the entire surface and that there are no dry spots.
Application	<p>Stir part A, add part B, and mix thoroughly for 3-4 minutes with a slow-speed drill/mixer. The minimum application temperature is +12°C, which applies to both the substrate and air temperature. The product's temperature should be above +15°C during use.</p> <p>The PU coating is fully cured after 7 days and must not be exposed to water spills, chemicals, or mechanical wear until complete curing is achieved. This could cause discoloration.</p>
Storage and Transport:	The product must be stored in a dry, frost-free place and in accordance with national regulations. Packaging must be kept tightly closed and stored in a dry area with consistent temperature. The product should be transported and stored standing, in a dry and frost-free environment.
Waste Disposal	Liquid uncured plastic should not be discharged into sewage systems or nature but should be delivered to an approved hazardous waste collection point. Uncured plastic can be delivered as residual waste to recycling stations, but it is recommended to contact the relevant station for specific advice, as local variations may apply.
	
Safety	The product may cause skin allergies, and appropriate gloves, work clothing, and goggles should be worn. See the safety data sheet for more details. Read the information on the packaging.

The information in this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished goods, and since the conditions under which they are used are often beyond our control, we cannot guarantee anything other than the product's quality. The products are supplied in accordance with our general terms for sales, delivery, and service unless otherwise agreed in writing. We reserve the right to make minor product changes and to update the specified data without prior notice. This data sheet replaces previous versions.

Contact Information

Gjøco AS, Galterud
Sagmoen 100, NO-2223 Galterud, Norway
Phone: +47 712 91 700
Email: office@gjoco.no

