

Product datasheet

Herregård Oljebeis Matt



Herregård Oljebeis Matt is a weather-resistant alkyd-modified stain for outdoor use. It is applied to new wood, timber, pressure-treated wood, and previously stained wood. Herregård Oljebeis Matt provides a matte and sophisticated appearance. It contains effective film-protecting agents against mold.

Revised 14.05.2025

Symbols




Technical data

Type:	Alkyd-modified stain
Color:	Base C and yellow transparent, mixed over Gjøcomix in selected colors (see color chart).
Gloss:	Matte 5-10 depending on the number of coats and substrate.
Density:	Approx. 1.01 kg/l
Application method:	Brush or roller. Spraying should be done by professionals.
Thinner/cleaning agent:	Water, cleaned with soap and water.
Recommended coverage:	
Planed wood:	8-10 m ² /liter
Unplaned wood:	5-8 m ² /liter
Recommended data for high-pressure sprayer:	
Nozzle:	0.015"; 0.38 mm
Spray angle:	65°-80°
Paint pressure:	150 kg/cm ² , 15 MPa
Drying time (23 °C, 50% R.H.):	
Dust dry:	6 hours. Low temperatures extend drying time.
Recoating interval, minimum:	12 hours. Depends on temperature, humidity, wind, and film thickness.
Minimum application temperature:	+5 °C. The substrate must be dry and free of frost.

Pretreatment

The surface must be clean and dry before starting the painting work. New or bare wood should be treated with 1 coat of Gjøco Oljegrønning Klar or Gjøco Aquagrønn Klar. It is easier to avoid streaks and achieve an even result when using Gjøco Oljegrønning Klar, as it is solvent-based and does not cause fiber

	<p>raising. New wood that has been untreated for more than 4 weeks should be cleaned and wire-brushed before priming. Previously stained wood should be cleaned with Gjøco Kraftvask to remove grease and contaminants. Weathered surfaces and worn-out stain should be wire-brushed or sanded to remove loose stain and wood fibers. Only spots should be stained before applying stain over the entire wall. All end grain must be well-saturated with primer, with 3-4 coats applied wet-on-wet. For planed wood and other smooth and/or hard surfaces, it may be necessary to wire-brush or sand to ensure proper adhesion. To achieve the best possible edge coverage, round sharp edges before priming.</p>
Directions for use	<p>For new unplanned wood, apply 2 coats. For new planed wood and timber, apply 3 coats. For previously stained surfaces, apply 1-2 coats as needed. Apply the stain along the length of the boards to avoid streaks. Herregård Oljebeis Matt dries faster than regular oil-based stain, so it is recommended to stain only 1-2 board lengths at a time to prevent streaks and overlap. This is especially important on planed wood. Ensure that all end grain is adequately saturated.</p>
Color	<p>The oil stain is transparent, and the color will therefore vary on different types of substrates; planed/unplaned, different wood species, pressure-treated, treated/untreated surfaces, etc. Always test a small sample first. Remember that the color will become stronger and darker with each additional coat. Use the same batch number for the same coat and surface to avoid color shade differences.</p>
Storage	<p>Seal the lid tightly when storing the stain to prevent spillage and drying out. The stain should be transported and stored upright, in a dry and frost-free environment.</p>
Disposal of waste	<p>Liquid paint should not be disposed of in sewage drains or the environment but should be delivered to an approved hazardous waste collection facility. Empty, clean, and dry plastic containers without handles can be disposed of as plastic waste.</p> <div data-bbox="555 1305 794 1386">  </div>
Other information	<p>The surface must be solid, clean, and dry before applying the oil stain. Stir well. Make sure to use the same batch number to avoid gloss and color differences. Surfaces previously treated with linseed oil paint/stain may cause blistering. Previously tar-treated surfaces may cause discoloration, especially noticeable on light colors. Dewfall on a half-dry surface may result in matte streaks. Do not use on frosted wood. Exposed walls typically wear faster than other walls and therefore require more frequent treatment. Packaging sizes: 2.7 and 9 liters.</p>
Safety	<p>See the safety data sheet for more information. Read the information on the packaging. EU limit for this product (cat. A/e): 130 g/l (2010). This product contains: <100 g/l VOC.</p>

The information in this data sheet is based on laboratory tests and practical experience. Our products are considered semi-finished goods, and since the conditions under which the products are used are often beyond our control, we cannot guarantee anything other than the quality of the product. The products are supplied in accordance with our general terms and conditions of sale, delivery, and service, unless otherwise agreed in writing. We reserve the right to make minor product changes and to alter the specified data without prior notice. This data sheet replaces previous versions and is automatically canceled 5 years after the issue date.

Contact information

Gjøco AS

Ørvegen 1160, 6639 Torvikbukt

Telephone: +47 712 91 700

E-mail: office@gjoco.no

