

Poliuretano Spray S-303 HFO

Isocianato H

DESCRIPTION

A polyurethane system made up of two components – a polyol mixture and an isocyanate – that is sprayed in-situ to form rigid closed-cell foams for thermal insulation purposes.

Poliuretano Spray S-303 HFO has been formulated using hydrofluoroolefins (HFOs) – fourth-generation foaming agents, which means its contribution to global warming is very low.



Green Products

At Synthesia Technology we are using recycled PET from plastic bottles in the production of polyols, a key raw material used in the manufacturing of high-performance insulation. We are demonstrating that it is possible to use plastic waste responsibly, upcycling it into brand-new products that help to reduce energy consumption and CO₂ emissions, for the benefit of all. In this way, we promote the development of a circular and sustainable economy.

Poliuretano Spray S-303 HFO is manufactured with:

23% of Recycled PET

17% of Products of renewable origin

Equivalent to 54 PET bottles per m² for applied foam**

* Based on a weight of 8,6 g per PET bottle

**Considering a thickness of 10 cm and an applied density of 40 kg/m³



AENOR N MARK


AENOR has certified our **Poliuretano Spray S-303 HFO** spray system with its product-quality N Mark under standard EN 14315-1 as a thermal insulation material for buildings. Contract No 020/000186.



Contract Nber: 020/000186
This component (A) is certified as a complete system with the component B ISOCIANATO H

KEYMARK

The **Poliuretano Spray S-303 HFO** spray system is CEN KEYMARK SCHEME-certified as a thermal insulation product that is compliant with standard EN 14315-1.



This technical information is, to the best of our knowledge and experience, accurate at the time of publication. Nothing herein is to be construed as a warranty, express or otherwise. It is the responsibility of recipient to test the suitability of our products for their own purpose, as individual conditions of storage, use, and application, as well as suggested formulations and recommendations, are beyond our control. It is the responsibility of the recipient of our products to ensure that applicable property rights, laws and legislation are observed. The information and data contained herein merely serve as general information, do not constitute sales specifications and may be updated without notice. To ensure you are viewing the most recent and accurate product information, visit <https://www.synthesia.com/en/products> or contact cservice@synthesia.com

Poliuretano Spray S-303 HFO

Isocianato H

NSAI Agrément

NSAI Agrément certifies that the **Poliuretano Spray S-303 HFO** spray system meets the requirements of the “**Building Regulations 1997 to 2019**” if applied as per the instructions set forth in Certificate 19/0414.



BBA Agrément

In the opinion of the BBA, **Poliuretano Spray S-303 HFO** projection system for suspended floors, pitched roofs and external walls if installed, used and maintained in accordance with certificates 22/6098 Product Sheet 1, 2 and 3, it can satisfy or contribute to satisfying the relevant requirements of the Building Regulations in the different regions of the UK.



COMPONENTS

COMPONENT A: Poliuretano Spray S-303 HFO

A mixture of polyols containing catalysts, flame-retardants and foaming agents (it contains HFOs).

COMPONENT B: Isocianato H

Polymeric methylene diphenyl diisocyanate (MDI).

APPLICATIONS

The **Poliuretano Spray** system is sprayed according to a mixing ratio of 1:1 by volume using heated, high-pressure equipment. Its main applications are the external thermal insulation of façades and the internal thermal insulation of ceilings. Once it has been sprayed on, its density ranges from 35 to 45 g/L.

Application advantages:

- Complete suppression of thermal bridges. Since it is continuous, the insulation does not have any joints or cracks.
- Good adhesion to the substrate. No glues or adhesives need to be used for installation.
- Possibility of insulating and waterproofing in the same process. This is due, on the one hand, to its watertight-, closed-cell structure and, on the other, to the continuous manner in which it is applied, which allows doing away with joints.
- Mobility. It can be taken to construction sites in no time, there being no need to haul to or store on the site bulky products as in the case of other insulating materials.
- Sealing of gaps, thus muffling the passage of sound.
- Increase in the floor space compared to other insulating materials.

This technical information is, to the best of our knowledge and experience, accurate at the time of publication. Nothing herein is to be construed as a warranty, express or otherwise. It is the responsibility of recipient to test the suitability of our products for their own purpose, as individual conditions of storage, use, and application, as well as suggested formulations and recommendations, are beyond our control. It is the responsibility of the recipient of our products to ensure that applicable property rights, laws and legislation are observed. The information and data contained herein merely serve as general information, do not constitute sales specifications and may be updated without notice. To ensure you are viewing the most recent and accurate product information, visit <https://www.synthesia.com/en/products> or contact cservice@synthesia.com

Poliuretano Spray S-303 HFO

Isocianato H

CHARACTERISTICS OF THE COMPONENTS

Characteristics	Units	H	S-303 HFO
Specific Weight 20°C	g/cm ³	1,23	1,14
Viscosity	cP	150-250 (25°C)	200-500 (22°C)
Free NCO content	%	30-32,5	-

SYSTEM SPECIFICATIONS

The specifications of the system were measured in a test vessel at 22°C with the mixing ratio specified in Synthesia Technology's standard (MANS -01) and as per Annex E of product standard EN 14315-1.

A/B mixing ratio: 1:1 by volume
1:1 ± 4 by weight

Specifications	Units	S-303 HFO-W	S-303 HFO-S
Cream time	s	3 ± 1	3 ± 1
Gel time	s	6 ± 2	7 ± 2
Set-to-touch time	s	8 ± 3	8 ± 3
Free density	g/L	33 ± 3	33 ± 3

PREPARATION OF THE SUBSTRATE

Surfaces should be clean, dry, and free of dust and grease so that the foam can properly adhere to the substrate; if the substrate is a metal, it should also be free of rusting. In favourable conditions, the **Poliuretano Spray** foam adheres well to most building materials. Even so, should its adhesion prove to be not strong enough, a suitable primer should be used, and a minimum spray density of 38 kg/m³ attained.

Nevertheless, we cannot guarantee that this system will adhere to all types of substrates and primers. Consequently, the user should carefully study each specific case.

Poliuretano Spray S-303 HFO

Isocianato H

SPRAYING PROCESS

The foam's performance is affected by quite a few factors, which are listed below:

- The atmospheric conditions: ambient/room and substrate-surface temperature and humidity and other environmental factors (wind...).
- The settings of the equipment. The correct mixing ratio.
- The type of application: vertical, horizontal, or upside down.
- The application method: coat thickness, use of varnish.

In order for the foam to have an optimal performance and properties, the application conditions listed in the following table should be taken into account:

	S-303 HFO-W	S-303 HFO-S
SETTINGS OF THE EQUIPMENT		
Component mixing ratio	1:1 by volume	
Temperature of the components	15 - 30°C	
Temperature of the hoses and pre-heaters	25 - 50°C	
Static pressure	1200 - 1800 psi / 80 - 120 bar	
Maximum difference in dynamic pressure between components	290 psi / 20 bar	
ENVIRONMENTAL CONDITIONS		
Ambient/room temperature	+5 to +30°C	+10 to +40°C
Wind speed	≤ 30 km/h	
SUBSTRATE CONDITIONS		
Temperature	+5 to +30 °C	+10 to +40 °C
Moisture	Porous substrates	≤ 20 %
	Non-porous substrates	No surface condensation

The coat thickness can be controlled without any problems and modified by varying the spray rate and/or the mixing chamber of the gun, and it should range from 10 to 20 mm.

Please note that the smaller the number of coats for the same thickness, the higher the foam's performance. However, it is not advisable to spray on coats having thicknesses exceeding 20 mm in order to prevent pockets and having issues owing to the strong exothermic characteristics of the reaction and thus for the foam to maintain its properties.

Poliuretano Spray S-303 HFO

Isocianato H

CHARACTERISTICS OF THE FOAM

Characteristics		Units	S-303 HFO
Closed cells	ISO 4590	%	≥ 90
Thermal resistance & thermal conductivity	EN 12667 EN 12939	-	See the table of characteristics below
Reaction to fire (exposed foam)	EN 13501-1	Euroclass	E (1)
Water absorption (Wp)	EN 1609	kg/m ²	≤ 0.2
Water vapour resistance factor (μ)	EN 12086	-	≥ 70
Side-perpendicular tensile strength	EN 1607	kPa	≥ 100 (A3)

(1) Test result valid for any spray thickness (test conducted with a thickness of 60 mm).

Table of characteristics

Sprayed-on CCC4 insulation foam (uncoated or open to diffusion).

e _p	25	30	35	40	45	50	55	60	65
λ _D	0,028	0,028	0,028	0,028	0,028	0,028	0,028	0,028	0,028
R _D	0,90	1,10	1,25	1,45	1,65	1,85	2,00	2,20	2,40
e _p	70	75	80	85	90	95	100	105	110
λ _D	0,028	0,028	0,026	0,026	0,026	0,026	0,026	0,026	0,026
R _D	2,55	2,75	3,10	3,25	3,45	3,65	3,85	4,05	4,25
e _p	115	120	125	130	135	140	145	150	155
λ _D	0,026	0,025	0,025	0,025	0,025	0,025	0,025	0,025	0,025
R _D	4,45	4,80	5,00	5,20	5,40	5,60	5,80	6,00	6,20
e _p	160	165	170	175	180	185	190	195	200
λ _D	0,025	0,025	0,025	0,025	0,025	0,025	0,025	0,025	0,025
R _D	6,45	6,65	6,85	7,05	7,25	7,45	7,65	7,85	8,05

e_p Thickness (mm)

λ_D Declared aged thermal conductivity (W/mK)

R_D Thermal resistance level (m²·K/W)

Poliuretano Spray S-303 HFO

Isocianato H

INDOOR AIR EMISSIONS (VOCs)

Regulation	Poliuretano Spray S-303 HFO
French VOC Regulation	Class A+
French CMR components	Compliant
Italian CAM Edilizia	Compliant
ABG/AgBB	Compliant
Belgian Regulation	Compliant
Indoor Air Comfort GOLD®	Compliant
Blue Angel (DE-UZ 132)	Compliant
BREEAM International	Exemplary level
LEED v4.1 BETA (outside U.S.)	Compliant

Report n° 392-2021-00618901_A issued by Eurofins.

SAFETY RECOMMENDATIONS

Poliuretano Spray S-303 HFO (Component A) causes skin irritation and severe ocular lesions. In addition, it can cause irreparable damage to health and to the aquatic environment.

Isocyanato H (Component B) causes skin, eye and airway irritation. It can also cause irreversible damage to human health by inhalation or through contact with the skin.

When working with the product, the workers should wear complete personal protective gear, including a full face-mask breathing apparatus (which should supply fresh air if working inside confined, unventilated spaces), protective workwear, and safety gloves. Any other workers who are not going to take part in the application of the product should stay clear from the area. In addition, additional ventilation might be required in the form of natural or forced draught ventilation to prevent gases from building up and moving into other occupied areas of the building during the spraying process.

In the case of already occupied buildings, a 24h waiting period before reoccupation is recommended.

When handling the system and/or the products, it is advisable to take all safety and precautionary measures described in each product's MSDS.

SUPPLY FORM

Check with the Sales Department the different supply formats.

Poliuretano Spray S-303 HFO

Isocianato H

STORAGE RECOMMENDATIONS

VERY IMPORTANT: The components of the **Poliuretano Spray S-303 HFO** system are sensitive to moisture, so they should be stored in airtight drums or tanks. **The storage temperature should fall within the following temperature range: +5 +35°C.** At lower temperatures, the viscosity of the polyols will increase considerably, thereby hindering application; in addition, the isocyanate might crystallise. Higher temperatures can cause changes in the polyols, a loss of the expanding agent, a greater consumption of product, the swelling of the drums, and uncontrolled foaming on insertion of the pump's suction tube in the drums. To prevent the latter, it is advisable to leave the drums sit for a while after having been carried by road in a well-ventilated, as-cool-as-possible area before starting to work with them.

If the drums are fitted with white plastic caps, special care should be taken when handling the latter as they are more fragile than metal caps and can become distorted.

In order for the system to maintain the aforementioned characteristics, the drums should be kept tightly closed when not in use.

Under proper storage conditions, the shelf lives are 4 months for S-303 HFO and 9 months for Component B (isocyanate).

Poliuretano Spray S-303 HFO

Isocianato H

APPENDIX: APPLICATION ISSUES

Our Sales and Technical Support Service is available to answer any questions you might have during the preparation of the product. Nevertheless, below we have listed some of the most common issues that can occur during the spraying process:

Issue	Possible cause	Solution
Irregularly shaped span	Improperly adjusted gun pin or dirt in the mixing chamber	Improperly adjusted gun pin or dirt in the mixing chamber
Span with colour veining	Poor mixture owing to components clogging the gun or having differences in viscosity	Poor mixture owing to components clogging the gun or having differences in viscosity
Poor, closed span	High component viscosity. Cold weather	High component viscosity. Cold weather
Very open span and misting	Too much air in the gun's nozzle Mixing pressure too high	Too much air in the gun's nozzle Mixing pressure too high
The material takes a while to react; it sags	Cold surface	Cold surface
Material sprayed too fast; irregular finish; misting	The pressure is too high	The pressure is too high
The material arrives at the surface looking granulated and clogs the gun	The temperature is too high	The temperature is too high
Air pockets form	The coats are more than 20mm thick	The coats are more than 20mm thick